



Rec'd PCT/PTO 03 MAR 2005  
PCT/EP 03/09803 10/526209



#2

INVESTOR IN PEOPLE




The Patent Office  
Concept House  
Cardiff Road  
Newport  
South Wales  
NP10 8QQ

I, the undersigned, being an officer duly authorised in accordance with Section 74(1) and (4) of the Deregulation & Contracting Out Act 1994, to sign and issue certificates on behalf of the Comptroller-General, hereby certify that annexed hereto is a true copy of the documents as originally filed in connection with the patent application identified therein.

In accordance with the Patents (Companies Re-registration) Rules 1982, if a company named in this certificate and any accompanying documents has re-registered under the Companies Act 1980 with the same name as that with which it was registered immediately before re-registration save for the substitution as, or inclusion as, the last part of the name of the words "public limited company" or their equivalents in Welsh, references to the name of the company in this certificate and any accompanying documents shall be treated as references to the name with which it is so re-registered.

In accordance with the rules, the words "public limited company" may be replaced by p.l.c., plc, P.L.C. or PLC.

Re-registration under the Companies Act does not constitute a new legal entity but merely subjects the company to certain additional company law rules.




Signed *Andrew Gensay*  
Dated 9 September 2003

PRIORITY DOCUMENT  
SUBMITTED OR TRANSMITTED IN  
COMPLIANCE WITH  
RULE 17.1(a) OR (b)

Best Available Copy

An Executive Agency of the Department of Trade and Industry



The Patent Office

1/77

The Patent Office  
Cardiff Road  
Newport  
Gwent NP9 1RH

# Request for grant of a patent

(See the notes on the back of this form. You can also get an explanatory leaflet from the Patent Office to help you fill in this form)

1. Your reference	3.76322		
2. Patent application number (The Patent Office will fill in this part)	0220681.1		
3. Full name, address and postcode of the or of each applicant (underline all surnames)	Borealis Technology OY PO Box 330 Fin-06101 Porvoo Finland		06SEP02 E746235 1 000027 P01/7700 0.00-0220681.1
Patents ADP number (if you know it)	7914617001		5 SEP 2002
If the applicant is a corporate body, give country/state of incorporation	Finland		
4. Title of the invention	Process		
5. Name of your agent (if you have one)	Frank B. Dehn & Co.		
"Address for service" in the United Kingdom to which all correspondence should be sent (including the postcode)	179 Queen Victoria Street London EC4V 4EL		
Patents ADP number (if you know it)	166001		
6. If you are declaring priority from one or more earlier patent applications, give the country and the date of filing of the or of each of these earlier applications and (if you know it) the or each application number	Country	Priority application number (if you know it)	Date of filing (day / month / year)
7. If this application is divided or otherwise derived from an earlier UK application, give the number and the filing date of the earlier application	Number of earlier application	Date of filing (day / month / year)	
8. Is a statement of inventorship and of right to grant of a patent required in support of this request? (Answer 'Yes' if: a) any applicant named in part 3 is not an inventor, or b) there is an inventor who is not named as an applicant, or c) any named applicant is a corporate body. See note (d))	yes		

76322.615

# PROCESS

5 This invention relates to a process for the  
preparation of an unsupported single site catalyst, to  
the use of the catalyst in olefin polymerisations and to  
the catalyst *per se*. In particular, the invention  
describes the use of an aluminoxane co-catalyst and  
Lewis base to form a particulate suspension which is  
10 subsequently reacted with a single site complex to form  
the catalyst species.

Many processes and catalysts are known for the  
preparation of homo and co-polymeric olefins. Ziegler-  
Natta catalyst compositions, developed in the 1950s,  
15 were found to be particularly useful in the preparation  
of polyolefins due to their high activity. As an  
alternative to Ziegler-Natta species Phillips developed  
catalyst systems based around chromium oxide compounds.

More recently, single-site catalysts, e.g.  
20 metallocenes, have been used to prepare polyolefins  
since they allow the preparation of polymers having  
narrow molecular weight distribution and compositional  
uniformity. Moreover, these features may be readily  
controlled using single site catalysts.

25 In the last few years, single-site catalysts have  
been supported on inorganic or polymeric supports and  
used in heterogeneous catalysis. Such supported  
catalyst species are known to perform better than their  
corresponding non-supported analogues since, *inter alia*,  
30 they give rise to polymer particles having better  
morphology. At present, supported single-site  
catalysts are routinely used in olefin polymerisation.  
Supports used may be polyolefinic or inorganic but it is  
conventional to use a silica or alumina support.

35 However, the preparation of supported catalysts is  
complicated and expensive. Before most supports can be  
impregnated with the actual single site species it is

necessary to calcinate the support. In this process the support is exposed to temperatures of up to 800°C so as to remove surface hydroxyl groups which could interfere with catalyst loading and subsequent polymerisation.

5 Once calcination has occurred the single site catalyst needs to be impregnated into the support. This process often results in catalyst wastage and of course requires the support to be porous. Moreover, catalyst left on the surface of a support rather than in a pore can cause  
10 hotspots in a reactor during polymerisation. Finally, the supports used are also expensive as they need to be pure and porous and also are made of potentially expensive material. Nevertheless, the skilled polymer chemist still prefers to use supported catalysts despite  
15 the above limitations due to the improvements in polymer properties which result.

It would be desirable however, if polymerisation could take place in the absence of a supported catalyst but still give rise to polymer particles which have the  
20 excellent particle morphology normally realised with a supported species. Also, polymers made using unsupported catalysts will obviously be free from any residual carrier material. In certain applications, e.g. film applications this may be important since in  
25 polymers made using conventional supported catalysts, particles of the carrier may be visible in the film.

It is generally believed that it is very difficult to obtain good particle morphology using an unsupported catalyst however the present inventors have surprisingly  
30 found that good particle morphology in the eventual polymer can be obtained when the catalyst is made by forming particles from the reaction of an aluminoxane with a Lewis base in a hydrocarbon solvent. Subsequently, the resulting particles may be reacted  
35 with a single site complex to form a suspension of small catalyst particles which may be used as an olefin polymerisation catalyst.

Whilst aluminoxane is a very common co-catalyst for olefin polymerisation and Lewis bases have been routinely used in polymerisations, never before has it been suggested that they may be used to form a suspension which may act, in combination with the single site complex, as a catalyst.

For example, in EP-A-630910 the use of a Lewis base in an olefin polymerisation is described however, the Lewis base is present to control the activity of the reaction rather than to form particles.

In WO 98/20045 certain Lewis bases are described as antifouling agents. In US 5892079 neutral Lewis bases are suggested as additives to accelerate the rate of polymerisation.

Thus, viewed from one aspect the invention provides a process for the preparation of an olefin polymerisation catalyst comprising:

- a) reacting an aluminoxane and a Lewis base in an optionally halogenated hydrocarbon solvent to form a particulate suspension;
- b) reacting said suspension with a metallocene complex in a hydrocarbon solvent; and optionally
- c) isolating the resulting olefin polymerisation catalyst.

Viewed from another aspect the invention provides a catalyst obtainable by, e.g. obtained by, a process as hereinbefore described.

Viewed from another aspect the invention provides the use of a catalyst as hereinbefore described in olefin polymerisation.



Viewed from a still yet further aspect the invention provides a process for the preparation of polyolefins comprising polymerising at least one olefin in the presence of an olefin polymerisation catalyst as hereinbefore described.

The aluminoxane employed in the manufacture of the particle suspension can be any conventional aluminoxane

as is known in the art.

Aluminoxanes are compounds with alternating aluminium and oxygen atoms generally compounds of formula I or II

5



10 where each R, which may be the same or different, is a C<sub>1-10</sub> alkyl group, and p is an integer having a value between 0 and 40). These compounds may be prepared by reaction of an aluminium alkyl with water. The production and use of aluminoxanes is described in the  
15 patent literature, especially the patent applications of Texas Alkyls, Albemarle, Ethyl, Phillips, Akzo Nobel, Exxon, Idemitsu Kosan, Witco, BASF and Mitsui.

Traditionally, the most widely used aluminoxane is methylalumoxane (MAO), an aluminoxane compound in which  
20 the R groups are methyls. Efforts have been made, however, to use aluminoxanes other than MAO. Thus, for example WO98/32775 (Borealis) proposes the use of metallocene procatalysts with alumoxanes in which R is a C<sub>2-10</sub> alkyl group, eg hexaisobutylalumoxane (HIBAO). In  
25 the present invention, it is preferred if the aluminoxane is MAO.

The optionally halogenated hydrocarbon solvent to be used in the first stage of the process must be one in which the reaction product of the Lewis base and  
30 aluminoxane is insoluble or only slightly soluble. This ensures the formation of a suspension. Suitable hydrocarbons therefore include C<sub>4-12</sub>-alkanes such as isobutane, pentane, hexane, heptane and octane, aryl hydrocarbons such as benzene, toluene and xylene and  
35 halogenated alkane/aryl hydrocarbons such as dichloromethane, dichloroethane, dichloropropane, chlorobenzene, dichlorobenzene and trichlorobenzene.

Mixtures of any of these solvents may also be employed. Preferably the solvent is aromatic, e.g. xylene. A particularly preferred solvent is toluene.

5 Whilst the solvent used in stage (b) of the process of the invention may be different from that employed in the first stage and may therefore be selected from any of those listed above, it is preferable if the same solvent is employed.

10 The Lewis base to be reacted with the aluminoxane is preferably an organic Lewis base and must comprise at least one free, lone pair of electrons. Preferably, the Lewis bases of use in the invention comprise aliphatic or aromatic amines, alcohols, thiols, aldehydes, ketones, carboxylic acids or ethers. These compounds  
15 may contain up to 20 carbon atoms, e.g. up to 10 carbon atoms. Particularly suitable Lewis bases include phenol, benzyl alcohol, aniline, benzylamine etc. In an especially preferred embodiment the Lewis base comprises at least two groups, either the same or different,  
20 comprising free lone pairs e.g. aliphatic or aromatic diamines or diols, triols, hydroxy ethers, etc or mixtures thereof. These compounds may contain up to 20 carbon atoms, e.g. up to 10 carbon atoms. Especially preferably therefore, the Lewis base is ethylene glycol,  
25 glycerol, triethanolamine, butanediol, 4,4'-isopropylidenediphenol, 3-hydroxypropylene oxide and 1,4-butanediol diglycidyl ether.

The ratio of Lewis base to metallocene can vary over a wide range but should be carefully controlled to  
30 ensure the formation of advantageous particles. Ideally, the ratio of aluminium in the aluminoxane to Lewis base is 1 to 100 mol/mol, preferably 5 to 40 mol/mol, especially 10 to 25 mol/mol. Higher ratios of aluminoxane to Lewis base may be employed especially  
35 when tri or higher "lone pair" functionalised Lewis bases are employed.

The solvent used for the Lewis base can be the same

or different as for the aluminoxane solution. The choice and amount of the solvent for the Lewis base depends on its solubility. The desired concentration will be set by the temperature of the solution so that the Lewis base is preferably dissolved.

The reaction of Lewis base and aluminoxane may take place at atmospheric pressure. The reaction temperature and time can vary over a wide range depending on the Lewis base employed but are preferably between -10°C to 80°C and 1 to 48 hours, especially between 40 to 70°C, e.g. 55°C and 10 hours to 25 hours, respectively.

By "metallocene" is here meant an  $\eta$ -ligand metal complex, e.g. an "open sandwich" or "half sandwich" compound in which the metal is complexed by a single  $\eta$ -ligand, a "sandwich" compound in which the metal is complexed by two or more  $\eta$ -ligands, a "handcuff" compound in which the metal is complexed by a bridged bis- $\eta$ -ligand or a "scorpionate" compound in which the metal is complexed by an  $\eta$ -ligand linked by a bridge to a  $\sigma$ -ligand.

Suitable metallocene complexes for inclusion in the catalyst of the invention include cyclopentadienyl, indenyl and fluorenyl species which are well known in the art. Examples of further  $\eta$ -ligands abound in the patent literature relating to metallocene and pseudo metallocene olefin polymerization (pro)catalysts, in particular that deriving from Exxon, Hoechst, Phillips, Dow, Chisso, Mitsui, Fina, BASF, Mitsubishi, Mobil, Targor, DSM and Borealis, eg WO96/23010, WO98/49208, WO99/12981, WO99/19335, WO97/28170, EP-A-423101, EP-A-537130, etc. as well as "Metallocenes" Vol. 1, Togni and Halterman (Eds.) Wiley-VCH, 1998.

Preferred metallocene complexes are bis(cyclopentadienyl) compounds wherein the cyclopentadienyl ring may comprise substituents such as siloxy groups or alkyl groups. A particularly preferred compound is bis(n-Bu-cyclopentadienyl) zirconium



dichloride.

5 The metal of use in the metallocene is selected from groups 3 to 8 of the periodic table, especially groups 4, 5 and 6. Suitable metals therefore include titanium, zirconium, hafnium and vanadium. The metals are typically coordinated to the  $\eta$ -ligands and also to sigma ligands such as amido, halo or hydrogen. Chloro sigma ligands are most preferred.

10 The amount of metallocene added to the suspension is linked to the amount of aluminoxane. The molar ratio between aluminum in the aluminoxane and the transition metal in metallocene can be in the range 1:1 to  $10^8$ :1. Typically however, the ratio is between 10:1 and  $10^5$ :1, preferably 20:1 to 1000:1, especially 50:1 to 100:1.  
15 Conveniently, the addition of the metallocene to the suspension formed in part (a) of the process of the invention occurs at the same temperature as the reaction of the aluminoxane and Lewis base. Process step (b) of the process of the invention may take from 1 to 5 hours, preferably 2 hours.  
20

The size of the resulting catalyst particles varies, *inter alia*, depending on the reaction equipment, how the reaction is performed (e.g. reaction temperature, component addition speed etc), stirring during reactant addition and stirring during reaction.  
25 More vigorous stirring gives rise to smaller catalyst particles. Lower reaction temperatures and slower component addition speeds give larger particles. Stirring of the reaction mixture is conveniently carried out using an anchor stirrer which may rotate at 100 RPM to 300 RPM, e.g. 250 RPM.  
30

35 The olefin to be polymerized by the olefin catalyst of the invention may be ethylene, propylene or a mixture of ethylene or propylene and another  $C_{2-10}$   $\alpha$ -olefin, for example, ethene, propene, n-but-1-ene, n-hex-1-ene, 4-methyl-pent-1-ene, n-oct-1-ene etc. The olefins polymerized may also include any compound which includes

unsaturated polymerizable groups. Thus for example unsaturated compounds, such as C<sub>6-20</sub> olefins (including cyclic and polycyclic olefins (e.g. norbornene)), and polyenes, especially C<sub>6-20</sub> dienes, may be included in a comonomer mixture with lower olefins, e.g. C<sub>2-5</sub> α-olefins. Diolefins (ie. dienes) are suitably used for introducing long chain branching into the resultant polymer. Examples of such dienes include α,ω linear dienes such as 1,5-hexadiene, 1,6-heptadiene, 1,8-nonadiene, 1,9-decadiene, etc. Preferably the olefin to be polymerised in ethene.

The catalysts of the invention may be used in solution, slurry or gas phase polymerisations and such polymerisations are well-known in the art. Slurry polymerisations are preferred and may be carried out in a loop reactor or continuous stirred tank reactor. For loop reactors, the reaction temperature will generally be in the range 60 to 110°C (e.g. 85-110°C), the reactor pressure will generally be in the range 5 to 80 bar (e.g. 50-65 bar), and the residence time will generally be in the range 0.3 to 5 hours (e.g. 0.5 to 2 hours). The diluent used will generally be an aliphatic hydrocarbon having a boiling point in the range -70 to +100°C. In a preferred embodiment, polymerization is effected under supercritical conditions. Under such conditions the diluent is preferably propane.

In gas phase reactors, the reaction temperature used will generally be in the range 60 to 115°C (e.g. 70 to 110°C), the reactor pressure will generally be in the range 10 to 25 bar, and the residence time will generally be 1 to 8 hours. The gas used will commonly be a non-reactive gas such as nitrogen together with monomer (e.g. ethylene).

Hydrogen may be used to control the molecular weight of polymer components as is known.

The polymers produced by the process of the invention may be utilised in a variety of fields such as

in the manufacture of films, pipe, sheets, tubes, containers, etc. The polymers are therefore suitable for blow moulding, injection moulding, rotomoulding etc.

5 In a preferred embodiment, the catalyst of the invention is prepolymerised prior to being used in a main polymerisation stage. It is believed that a prepolymerisation stage may allow improvements in particle morphology. Prepolymerisation is effected as is known in the art by contacting the initially formed catalyst with a monomer or monomers and allowing a small amount of polymerisation to take place. Suitable monomers are ethylene, propylene etc however, in a preferred embodiment the olefin employed is one which gives rise to a polymer of higher melting point than that of the main polymerisation. Suitable monomers in this regard are 3-methylpentene and vinylcyclohexane.

10 Viewed from a further aspect the invention provides a process for the preparation of a prepolymerised olefin polymerisation catalyst comprising:

- 20 a) reacting an aluminoxane and a Lewis base in an optionally halogenated hydrocarbon solvent to form a particulate suspension;
- b) reacting said suspension with a metallocene complex in an optionally halogenated hydrocarbon solvent to form a catalyst;
- 25 c) prepolymerising said catalyst in the presence of an olefin; and optionally
- d) isolating the prepolymerised catalyst.

The invention is further described below with reference to the following non-limiting examples.

#### Example 1 - Comparative

35 20.4 ml of 30% MAO was mixed with 0.188 mg of bis(n-butylcyclopentadienyl)zirconium dichloride ( $Al/Zr = 200$ ) in 5.1 ml of toluene. The reaction was allowed to run for 2 hours at room temperature. 15.8 ml of this

complex was added to 10.2 g of Sylopol 55SJ Silica and mixed for 2 h at room temperature. The product was dried under nitrogen at a maximum of 70°C.

5     **Example 2 - Unsupported catalyst**

1.62 g of bisphenol-A in 130 ml of toluene was added slowly to 14.2 g of 30% MAO solution. The mixture was stirred for 20 h at 250 RPM and 55°C during which time  
10     solid particles were formed. 0.144 g of bis(n-butylcyclopentadienyl)zirconium dichloride (Al/Zr = 200) in 20 ml toluene was added to the reaction mixture and stirred for 2 h at 55°C. After drying 6.2 g of catalyst was collected.

15

**Example 3 - Unsupported catalyst prepolymerised**

1.62 g of bisphenol-A in 130 ml of toluene was added slowly to 14.2 g of 30% MAO solution. The mixture was  
20     stirred for 20 h at 55°C during which time solid particles were formed. 0.144 g of bis(n-butylcyclopentadienyl)zirconium dichloride (Al/Zr = 200) in 20 ml toluene was added to the reaction mixture and stirred for 2 g at 55°C. After drying 6.2 g of catalyst  
25     was collected. Prepolymerisation was carried out at room temperature by adding slowly 6 g of vinylcyclohexane into the catalyst/toluene suspension and mixing for one hour. After drying 10 g of prepolymerised catalyst was collected.

30

**Example 4 - Polymerisation**

Bench scale slurry polymerisations were carried out in a 2L reactor using the Isobutane, 1000ml, ethylene monomer  
35     (7.5 bar) at a total pressure of 23.5 bar, run time 60 mins at 85°C.

Cat.	Activity (kgPE/gcath)	Comments
Ex. 1	1.5	Good Morphology, no fouling
Ex. 2	0.7	No fouling, morphology acceptable with some bigger particles
Ex. 3	2.0	Slight fouling, morphology, acceptable

5

## Claims

1. A process for the preparation of an olefin polymerisation catalyst comprising:

5. a) reacting an aluminoxane and a Lewis base in an optionally halogenated hydrocarbon solvent to form a particulate suspension;

b) reacting said suspension with a metallocene complex in an optionally halogenated hydrocarbon solvent; and optionally

10 c) isolating the olefin polymerisation catalyst.

2. A process as claimed in claim 1 wherein said aluminoxane is MAO.

15 3. A process as claimed in any one of claims 1 or 2 wherein the optionally halogenated hydrocarbon solvent used during step a) is an optionally halogenated C<sub>4-12</sub> alkane or C<sub>6-12</sub> arylene.

20 4. A process as claimed in claim 3 wherein said hydrocarbon solvent is toluene or xylene.

25 5. A process as claimed in any one of claims 1 to 4 wherein the solvent employed in step b) is the same as that employed in step a).

30 6. A process as claimed in any one of claims 1 to 5 wherein said Lewis base is an aliphatic or aromatic amine, alcohol, thiol, aldehyde, ketone, carboxylic acid or ether or mixture thereof.

35 7. A process as claimed in claim 6 wherein said Lewis base is phenol, benzyl alcohol, aniline or benzylamine or mixture thereof.

8. A process as claimed in claim 6 wherein said Lewis

base aliphatic or aromatic diamines, diol, triol, hydroxy ether or mixtures thereof.

5 9. A process as claimed in claim 8 wherein said Lewis base is ethylene glycol, glycerol, triethanolamine, butanediol, 4,4'-isopropylidenediphenol, 3-hydroxypropylene oxide or 1,4-butanediol diglycidyl ether.

10 10. A process as claimed in any one of claims 1 to 9 wherein the ratio of aluminium in the aluminoxane to Lewis base is 5 to 40 mol/mol.

15 11. A process as claimed in any one of claims 1 to 10 wherein the metallocene complex is bis(n-Bu-cyclopentadienyl) zirconium dichloride.

20 12. A process as claimed in any one of claims 1 to 11 wherein the molar ratio between aluminium in the aluminoxane and the transition metal in metallocene is in the range 20:1 to 1000:1.

25 13. A catalyst obtainable a process as claimed in any one of claims 1 to 12.

14. The use of a catalyst as claimed in claim 13 in olefin polymerisation.

30 15. A process for the preparation of polyolefins comprising polymerising at least one olefin in the presence of an olefin polymerisation catalyst as claimed in claim 13.

35 16. A process for the preparation of a prepolymerised olefin polymerisation catalyst comprising:

a) reacting an aluminoxane and a Lewis base in an optionally substituted hydrocarbon solvent to form a

particulate suspension;

b) reacting said suspension with a metallocene complex in an optionally substituted hydrocarbon solvent to form a catalyst;

5 c) prepolymerising said catalyst in the presence of an olefin; and optionally

d) isolating the prepolymerised catalyst.



Abstract

Process

- 5 A process for the preparation of an olefin  
polymerisation catalyst comprising:
- a) reacting an aluminoxane and a Lewis base in an  
optionally halogenated hydrocarbon solvent to form a  
particulate suspension;
  - 10 b) reacting said suspension with a metallocene  
complex in an optionally halogenated hydrocarbon  
solvent; and optionally
  - c) isolating the olefin polymerisation catalyst.

**This Page is Inserted by IFW Indexing and Scanning  
Operations and is not part of the Official Record**

**BEST AVAILABLE IMAGES**

Defective images within this document are accurate representations of the original documents submitted by the applicant.

Defects in the images include but are not limited to the items checked:

- ☐ **BLACK BORDERS**
- ☐ **IMAGE CUT OFF AT TOP, BOTTOM OR SIDES**
- ☐ **FADED TEXT OR DRAWING**
- ☐ **BLURRED OR ILLEGIBLE TEXT OR DRAWING**
- ☐ **SKEWED/SLANTED IMAGES**
- ☐ **COLOR OR BLACK AND WHITE PHOTOGRAPHS**
- ☐ **GRAY SCALE DOCUMENTS**
- ☒ **LINES OR MARKS ON ORIGINAL DOCUMENT**
- ☐ **REFERENCE(S) OR EXHIBIT(S) SUBMITTED ARE POOR QUALITY**
- ☐ **OTHER:** \_\_\_\_\_

**IMAGES ARE BEST AVAILABLE COPY.**

**As rescanning these documents will not correct the image problems checked, please do not report these problems to the IFW Image Problem Mailbox.**